

FILM
INSERT
HERE

Interior Side

Benefits and selection criteria

- Shields >99% of UV radiation, helping to reduce fading of valuables, fabrics and furnishings**
- Reduction of hot spots helps increase HVAC efficiency and lower energy costs
- Exterior installation provides protection for hard to reach locations
- Provides the highest level of daytime privacy with optical transparency
- Used where an exterior application is critical, and unsurpassed heat and glare reduction are desired for rapid return on investment



FILM INSERT HERE

Exterior Side

Performance Data

	% Total Solar Transmittance	% Total Solar Reflectance	% Total Solar Absorbance	% Visible Light Transmittance	% Visible Reflectance (exterior)	% Visible Reflectance (interior)	Winter U-value	Shading Coefficient	% Ultraviolet Ray Protection (wavelengths 300-380nm)	Emissivity	Solar Heat Gain Coefficient	% Total Solar Energy Rejected	Light-to-Solar Heat Gain Ratio (LSG)	% Summer Solar Heat Gain Reduction	% Winter Heat Loss Reduction	% Glare Reduction
Clear Glass 1/4" (6mm) single pane	77	7	16	88	8	8	1.03	0.94	38	0.84	0.82	19	1.07	-	-	-
Clear Glass 1/4" (6mm) dual pane	61	11	28	79	14	14	0.47	0.81	54	0.84	0.70	30	1.13	-	-	-
RHE20 ER 1/4" (6mm) clear single pane	11	63	26	15	62	57	1.02	0.22	>99	0.71	0.19	81	0.79	77	1	83
RHE20 ER 1/4" (6mm) clear dual pane	9	63	28	14	62	55	0.47	0.16	>99	0.71	0.14	86	1.00	80	0	82

The solar performance data reported for LLumar architectural window films was captured using the National Fenestration Rating Council's (NFRC) standard guidelines for window film solar performance measurement. All safety and performance data has been measured in accordance with ASTM, ASHRAE, AIMCAL and ANSI standards using NFRC methodology with Lawrence Berkeley National Lab's WINDOW Fenestration Analysis Software. Reported values are taken from representative product samples and are subject to normal manufacturing variances. Actual performance will vary based on a number of factors, including glass type and properties.